

# 1.2 Definition and Basic Properties

## **Definition of a Polymer**

definition of a polymer according to Hermann Staudinger:


"A polymer is a large molecule constituted from (identical) smaller structural 'repeating units' with a length sufficient such that molecules with n and n+1 repeating units are indistinguishable"








- different from many natural macromolecules, natural and synthetic polymers are "polydisperse"
- since properties are indistinguishable, polymers are also inseparable

## Influence of Chain Length on Physical Properties










number of C atoms	aggregation state (25 °C)	example	usecase
1-4	gas	propane	gaseous fuel
5-15	low-viscosity liquid	gasoline	liquid fuel
16-25	high-viscosity liquid	motor oil	oils and greases
20-50	soft solid	paraffin wax	candles and coatings
> 1000	tough plastic material	polyethylene	bottles and toys


• increasing cohesive energy with increasing molecular weight (Chapter 4.1)

# Polymer Types, Architectures, Microstructures

homopolymers: one type of repeating units (but different architectures)



## Importance of Polymer Chain Architecture



• the polymer chain architecture affects the solidification of the polymers


## **Condensed States of Polymers**


viscous liquids





semi-crystalline

elastomers or thermosets



















• polymers are versatile materials with unique mechanical properties not shown by other materials classes

## **Amorphous, Glassy Polymers**

- hard solids, rigid (typical Young's modulus of 2-3 GPa)
- plastic behaviour, i.e. polycarbonate (PC), or more brittle behaviour, i.e. PS or PMMA
- generally transparent, amorphous (no structure that can scatter or absorb light)
- opaque, if fillers or pigments are added



amorphous, glassy














## **Semi-Crystalline Polymers**

- more or less rigid solids (Young's modulus can range from 0.1 to > 5 GPa depending on crystallinity, orientation and  $T_g$  of the amorphous phase)
- resistance to rupture, resistance to solvents
- generally opaque, depending on the microstructure














## **Examples of Thermosets**

- resins typically low in molecular weight and low in viscosity
- cross-linked during processing by applying heat or irradiation (e.g. UV)

#### **Thermosets**









epoxy resins, unsaturead polyesters (composites)







melamine



PUR

often good chemical and thermal resistance

## One Example of an Elastomer

- amorphous polymers with low glass transition temperatures
- slightly cross-linked into a network structure

#### elastomers











• soft, elastic materials (Chapter 5.1)



## The Polymerization Reaction

• polymer chain architecture, chemical composition, molecular weight, molecular weight distribution are all generated during the polymerisation reaction (Chapter 6.1)

• chemical formulae: the repeating unit is indicated in brackets.

Constitutive unit (CH<sub>2</sub>)

polymerization polymer backbone degree of polymer

monomer

ethylene


 usually, hydrogen atoms are omitted for clarity: polymerization


polymer

polyethylene (PE)

## Chain Configuration and Isomerism: Sequence Isomerism

- physical properties of polymeric systems are strongly affected by chain configuration and different forms of isomerism, i.e. the exact 3D arrangement of atoms or groups bound to a central atom
- built-in properties during polymerisation: no interconversion of isomers possible for a polymer chain






- examples: polystyrene, polypropylene, poly(methyl methacrylate), poly(vinyl chloride), ...
- head-to-tail addition is the predominant mode of propagation in chain growth polymerisations


## Constitutional (Structural) Isomerism in Polyisoprene

polyisoprene (PI) is obtained in different forms depending on the polymerisation conditions



• only cis-1,4-polyisoprene is produced at large scale with major application in tires


## One Example of an Elastomer



• two naturally occurring polyisoprenes, but two very different materials!

## Stereoisomerism / Tacticity


• tacticity refers to the stereoregularity of the substituted backbone atoms, i.e. to the manner of how the pendant groups (R) are arranged along the polymer chain backbone



• tacticity has huge impact on the physical properties of polymer materials (see crystallization, Chapter 4.3)

## Nomenclature of Single-Strand Polymers


- attachement of the prefix "poly" to the name of the monomer examples: polystyrene (PS), poly(vinyl chloride) (PVC), poly(etyhelene terephthalate) (PET)
- **systematic nomenclature** as defined by the *International Union of Pure and Applied Chemistry* (IUPAC) based on the identification of a preferred repeating unit.



example:  $\alpha$ -acetyl- $\omega$ -methoxy-poly(oxyethyleneoxyterephthaloyl)

## Nomenclature of Copolymers

random copolymer




(CN)<sub>X</sub>

poly(acrylonitrile-co-styrene)

SAN

multiblock copolymer







poly(polyethylene-b-polypropylene)



PP-b

branched copolymer






poly(butadiene-g-polystyrene)



"high-impact Polystyrene" (HIPS)

## Molecular Weight (MW) and Molecular Weight Distribution (MWD)

- polymers do not have defined molar masses but molecular weight distributions (MWD)
- different molecular weight averages, width, and shape
- molecular weight averages are moments of the molecular weight distribution



#### number average molecular weight

$$\overline{M}_n = \frac{\sum n_i M_i}{\sum n_i}$$

#### weight average molecular weight

$$\overline{M}_{w} = \frac{\sum n_{i} M_{i}^{2}}{\sum n_{i} M_{i}}$$

dispersity (formerly, polydispersity index)


$$\boldsymbol{\mathcal{D}} = \frac{\overline{M}_{w}}{\overline{M}_{n}}$$


ullet moreover, z-average molecular weight,  $\overline{M}_{z}$ , and viscosity average molecular weight,  $\overline{M}_{v}$  (Chapter 2.4)

# Number Average and Weight Average Molecular Weight



## Number Average and Weight Average Molecular Weight





$$\overline{M_n} = \frac{\sum n_i M_i}{\sum n_i} = \frac{8 \cdot 5000}{8} = 5000$$

$$\overline{M_w} = \frac{\sum n_i M_i^2}{\sum n_i M_i} = \frac{8 \cdot 5000^2}{8 \cdot 5000} = 5000$$

$$\overline{M_n} = \frac{\sum n_i M_i}{\sum n_i} = \frac{4 \cdot 9000 + 4 \cdot 1000}{4 + 4} = 5000$$

$$D = \frac{\overline{M_w}}{\overline{M_n}} = 1.64$$

$$\overline{M_w} = \frac{\sum n_i M_i^2}{\sum n_i M_i} = \frac{4 - 9000^2 + 4 \cdot 1000^2}{4 \cdot 9000 + 4 \cdot 1000} = 8200$$

$$\mathbf{D} = \frac{\overline{M_w}}{\overline{M_n}} = 1$$

molecularly uniform (monodisperse)

$$\mathcal{D} = \frac{\overline{M_w}}{\overline{M_n}} = 1.64$$

disperse

## Important Consequences of High Molar Mass

#### 1. Physicochemical Properties

- absence of a precise relation between  $T_m$  and M (Chapter 4.3)
- absence of a gaseous phase (Chapter 4.1)
- dominant chain entropy impacting both thermodynamics and mechanics (Chapter 5.1)

#### 2. Processing

- high viscosity (in solution and in the molten state) (Chapter 5.2)
- energy storage capacity in the molten state (viscoelasticity) (Chapter 5.2)
- capability of film and fiber formation from the molten state (viscoelasticity) (Chapter 6)

#### 3. Viscoelastic and Mechanical Properties

- spectrum of relaxation times (Chapter 5.2)
- vitrification (Chapter 4.2)
- elongation at break and high strength (Chapter 5.3)

## **Thermal Transitions of Polymers**

 abrupt transformation from glassy (hard) to soft state


onset of chain motion

**(Chapter 4.3)** 









 $||T_{g},T_{m}||$ 







polymer melt (Chapter 5.2)

 formation of ordered crystalline domains


(Chapter 4.4)



amorphous, glassy



semi-crystalline





monocrystalline



## **Thermal Transitions of Polymers**


analysis of thermal transitions with Differential Scanning Calorimetry (DSC) (Travaux Pratique)





• both  $T_m$  and  $T_g$  are important parameters that characterise a given polymer

## Classification of Polymer Materials According to Structure



## **Unique Mechanical Properties**

• polymers show unique mechanical properties not shown by other materials classes (see Chapter 5)

## rubber elasticity



specific to polymers

## viscoelasticity



important for processing

## plasticity





ductile behaviour


• strength, toughness, impact resistance, ductility, melt elasticity increase with molecular weight

# **Synthetic Polymers - Structure & Properties**

### **Thermoplastics**









**Elastomers** 



**Thermosets** 







## Summary

- polymers, macromolecules: recognized in the 1920's that they consist of covalently bonded repetitive sequences of subunits derived from monomers
- polymers are characterised by a molecular weight distribution, and not by a defined molar mass
- first systematic synthesis in 1938 (Nylon 6,6).
- polymer chemical structures defined by: composition, configuration (isomers), architectures,
   copolymers, branching, crosslinking etc.
- notion of glass transition temperature and melting temperature
- differentiation of thermoplastics, elastomers, and thermosets