


2023 Summer School: Tribology and Surfaces InteractionsJuly 3rd-7th, 2023 – Visp, Switzerland



Surfaces & Friction

Julien Fontaine

CNRS Research Scientist LTDS Ecole Centrale de Lyon

Laboratoire de Tribologie et Dynamique des Systèmes

LTDS UMR 5513

http://ltds.ec-lyon.fr









Introduction

Tribology:

science of contact, friction, wear and lubrication

Probably the key of most ancient techniques (stone tools, fire, wheel...)
yet a very recent science: « Tribology » invented in 1956...

- Solids are contacting through their *surfaces*, forming a *sliding interface*
- The surfaces' interactions are thus controlling/affecting the *friction* (and wear) between solids



Summary

♥ Dealing with surfaces...

- What is a « surface »? How to describe it?
- What are the key properties of a surface?
- ✓ How to characterise a surface?


Influence of surfaces on friction

- What is « Friction »?
- How can friction be affected by surfaces?
- How to study surface-related friction phenomena?

Case-study

Solid lubrication processes of Diamond-Like Carbon





Surfaces & Friction Dealing with surfaces...

Part 1

Laboratoire de Tribologie et Dynamique des Systèmes

LTDS UMR 5513

http://ltds.ec-lyon.fr









What is a surface?

« God created solids, but the devil made their surfaces » (Gott schuf das Volumen, der Teufel die Oberfläche) Wolfgang Pauli

Interface between two phases (or between a phase and vacuum)

- Surface = discontinuity of matter!
- Describing the solid before considering its surface!
 - ☐ You will bords
 ☐ You will be presented a second of the present of the pr
 - Strongly dependent on the material considered: metal, ceramic, polymer...
 - ho Key-role of the structure of matter at larger scales (nm \rightarrow μ m)



Cohesion of solids

Cohesion of solid: interactions between atoms or molecules

"Strong" interactions inside molecules or solids, "Weak" interactions between molecules or solids

- Chemical bonds: electron charge distributions of the atoms (atomic orbitals) is completely changed
- Physical "bonds": atoms/molecules remain distinct entities
- Yet physical binding may be quite strong as well...




Cohesion of solids: chemical bonds

- Strong chemical bonds: atomic interactions through electrons (change in shape and occupation of atomic orbitals)
 - lonic bond: exchange of electrons between two atoms Example: Sodium Chloride (salt!)

$$Na + Cl \rightarrow Na^+ + Cl^- \rightarrow NaCl$$

Covalent bond: sharing of electrons between two atoms



Metallic bonding: bonding electrons are delocalised over a lattice of atoms, creating a « gas of electrons » The behaviour of this gas and its interactions with the lattice controls the metal properties



Cohesion of solids: intermolecular forces

- Intermolecular bonding: involves electrostatic interactions between atoms and/or molecules
 - Involving charged atoms/molecules: Charge-charge interactions (Coulomb forces) or charge-dipole interactions
 - Involving polar molecules: Dipole-dipole, dipole-charge or dipole-induced dipole interactions (Van der Waals forces)
 - Polar molecules: distribution of charges within the molecule
 - Dipoles may be inherent to the structure of a molecule, or may be induced by the surrounding environment
- Depending on the type of interactions involved, **different** strengths and ranges will be observed...



The key-role of defects


- Solids are the result of a fabrication process they can't be perfect!
- Several types of defects can be found in crystalline materials:
 - Point defects (0D): vacancies or impurities (solid solutions)

 - Planar defects (2D): grain boundaries
 - Bulk defects (3D): voids or precipitates
- All these defects may affect the properties of the solid, especially hardness (while elastic modulus is controlled by interatomic or intermolecular forces)



The key-role of microstructure

- Many engineering materials are alloys
- They consist in an assembly of grains, with different orientations, that might be of different phases
- The nature, size and distribution of these phases control the mechanical behaviour of the material: hardness, toughness...




- Study of microsctrure:
 - Diffraction (XRD) for cristallography
 - Microscopy on cross-section (optical or electron: SEM), EBSD
 - X-Ray or TEM tomography



Describing a solid surface

- Machining process or fabrication process lead to gradients in the microstructure: *e.g.* change in grain size close to the surface...
- Since the surface is an interface with the environment, chemical reactions may occur at the surface: oxide layers, adventitious carbon...




Even for monocrystalline solids, the edges of a periodic lattice are not favorable: promote "surface reconstruction"

→ always some roughness!



Investigating surface topography

- Surfaces always exhibit some roughness...
- Critical role of the considered scale:



- The probe size is thus critical Many techniques available!
 - ▼ Tactile profilometry: from simple stylus to Atomic Force Microscopy (AFM)
 - Laser beam profilometry
 - Optical methods: interferometric microscopy, confocal microscopy...
- Don't forget to look at surface morphology!(e.g. optical or electron microscopy)



Investigating surface topography

- Parameters describing the surface:
 - Height characteristics
 - Arithmetical mean height

$$R_a = \frac{1}{L} \int_0^L |z| \, \mathrm{d}x$$

Root mean square roughness

$$R_q = \sqrt{\frac{1}{L} \int_0^L z^2 \, \mathrm{d}x}$$

- Maximum peak to valley, skewness (asymmetry), kurtosis...
- Spatial characteristics
 - Autocorrelation function, Power spectral density function...
- Multiscale characterisation
 - Fourier transformation, wavelet transformation...




Investigating surface chemistry

- Knowing the composition and/or chemistry of a surface is critical for understanding its properties
- Many surface characterisation techniques are available:
 - SEM coupled with EDX (Energy Dispersive X-ray spectroscopy)
 - ▼ Vibrational spectroscopies: Raman, FTIR...
 - ♥ Glow Discharge Optical Emission Spectroscopy (GDOES)
 - Secondary Ion Mass Spectrocopy (SIMS), static (ToF-SIMS) or dynamic
 - X-Ray Photoelectron Spectroscopy (XPS), Auger Electron Spectrocopy (AES)
 - ▼ Electron Energy Loss Spectroscopy (EELS) in transmission or reflection



Surface energy

- Surface energy corresponds to the disruption of interatomic or intermolecular bonds due to the surface creation
- Equivalence between surface energy (J/m²) and surface tension (N/m): Increasing the size of a surface corresponds to the work of a force
- Measuring surface energy:
 - **Contact angle measurements**
 - Liquid droplet on a surface
 - Young's equation: $\cos \theta_c = \frac{\gamma_{SG} \gamma_{SL}}{\gamma_{LG}}$
 - Work of adhesion: $W_{adh} = \gamma_{LG} \left(1 + \cos \theta_c \right)$




air

liquid

- Surface tension measurements (Wilhelmy plate tensiometer)
 - Immersion of a plate with measurement of undergone force
 - $\gamma = \frac{F}{l\cos\theta}, \text{ where } l \text{ is the perimeter}$





Surfaces & Friction Influence of surfaces on friction

Part 2

Laboratoire de Tribologie et Dynamique des Systèmes

LTDS UMR 5513

http://ltds.ec-lyon.fr











Defining friction...

Friction: the force resisting to relative motion between solids






- Early laws of dry friction Da Vinci, Amonton, Coulomb
 - Friction force is proportional to load
 - Friction force is independent of contact area
 - Friction force is independent of sliding velocity
- Definition of the **coefficient of friction** μ *Ratio of the tangential force to the normal force:*


$$\mu = \frac{F_t}{F_n}$$



Defining friction...

Friction: the force resisting to relative motion between solids





- Early laws of dry friction Da Vinci, Amonton, Coulomb
 - Friction force is proportional to load
 - Friction force is independent of contact area
 - Friction force is independent of sliding velocity
- No effect of apparent contact area!


Due to roughness, only asperities are touching...
Real vs. apparent contact area


 $A_r \neq A_{app}$



Defining friction...

Friction: the force resisting to relative motion between solids





- Early laws of dry friction Da Vinci, Amonton, Coulomb
 - Friction force is proportional to load
 - Friction force is independent of contact area
 - Friction force is independent of sliding velocity
- No velocity effect proposed, but:
 Static friction ≥ Sliding friction (or "kinetic" or "dynamic")
 Static friction: maximum friction force before sliding occurs




The challenge of lubrication: Velocity accommodation


- Lubrication with oils or liquids: a fluid film separates the solids, allowing an easy shear of the sliding interface
 - Hydrodynamic lubrication: thickness of the fluid film is large compared to the surface roughness
 - Elasto-hydrodynamic lubrication (EHD or EHL): elastic deformation of solid surfaces, creating
 - Mixed Lubrication: some asperity contact, but part of the load is carried by the fluid
 - Boundary lubrication: most of the load is carried by contacting asperities, which are surrounded by the fluid
- Solid lubrication: a material (often a coating) provides an easy shear of the sliding interface




Velocity accommodation in "dry" contacts

- In "dry" or "solid" contacts, when solid asperities interacts, shear occurs where it's easier!
- In case of seizure, breaking of adhesive junctions
 - at initial interface (1)
 - inside the weakest material (2) (depending on hardness and brittleness)
- With solid lubricants, shearing of interfacial films:
 - "Intrafilm flow" or "interfilm sliding"
- General case: shearing of debris or trapped particles → third body concept










What may be found in a "dry" contact?


- Flow from one solid to the other
- Compaction of wear debris
- Build-up of « tribofilms » or « transfer layer »
- Chemical reactions between contacting bodies or with the environment





Origins of friction force

Contributions to the friction force (Bowden & Tabor):




- Adhesion: shearing of adhesive junctions $F_{adh} = A_r \cdot \tau \text{, with } A_r \text{: real contact area, } \tau \text{: interfacial shear strength}$
- Plastic deformations
 - Macroscopic: ploughing abrasion of the softer body
 - Microscopic: plastic deformation of contacting asperities



Dry friction of metals: adhesion

Adhesive phenomena between asperities (Rabinowicz)



- Release of adhesive junctions:
 - Controlled by surface energy → strength of interface
 - Controlled by hardness → strength of asperities
- Empirical formula based on experimental results:


$$\mu \simeq 0.3 + C_1 \frac{W_{12}}{H}$$
, with $W_{12} = C_2 \left(\gamma_1 + \gamma_2 \right)$
$$\mu \simeq 0.3 + C_1 C_2 \frac{\gamma_1 + \gamma_2}{H}$$

 W_{12} : work of adhesion – γ_1, γ_2 : surface energies C_1 : geometrical constant – C_2 : miscibility constant H: hardness of softer body



Dry friction of metals: adhesion

Adhesive phenomena between asperities (Rabinowicz)



<i></i> ∼	0.3 +	CC	γ_1	$+\gamma_2$
μ —	0.5 +	c_1c_2		H


Condition	Symbol	Measured value of C_2	
Identical	0	1.00	
Compatible	ŏ	0.50	
Limited compatibility		0.32	
Very limited compatibility	~	0.20	
Incompatible	ě	0.125	

Symbol	Metallurgical solubility	Metallurgical compatibility	Sliding compatibility	Anticipated wear
0	100% Above 1%	Identical Soluble	Very poor Poor	Very high High
⊚ • •	0.1–1%	Intermediate soluble	Intermediate	Intermediate
	Below 0.1%	Intermediate insoluble	Intermediate or good	Intermediate or low
	Two liquid phases	Insoluble	Very good	Very low




Controlling dry friction: solid lubrication


- ☐ How to reduce dry friction of metals? (Bowden & Tabor).
 - Soft metal film Playing with A_r & τ in $F_t = A_r \cdot \tau$



au high A_r small




au small A_r high



au small A_r small


- General case with solid lubricants (Holmberg & Matthews)
 - Soft thin coating providing easy shear
 - Hard and stiff substrates (or underlayers)





The limits of Coulomb's law

Friction force is not always proportional to load: $\mu \neq \frac{F_t}{F_n}$



Force Normale

- Example: affine behaviour
 - $\mathbf{F}_t = \mu \cdot F_n + F_{t_0}$: Threshold in interfacial shear strength?
 - $F_t = \mu \left(F_n + F_{n_0} \right)$: Adhesive forces added to normal force?



The limits of Coulomb's law


▼ Both tangential & normal force are proportional to contact area

$$F_t = A_r \cdot \tau \text{ and } F_n = A_r \cdot P$$

$$\mu = \frac{F_t}{F_n} = \frac{\tau}{P}$$

If μ is changing with normal load, or contact pressure P, then it means that τ depends on contact pressure P

Example with MoS₂ solid lubricant coatings



e.g.
$$\tau = \tau_0 + \alpha P$$
 implies that $\mu = \frac{\tau_0}{P} + \alpha$ (Singer)



Key role of interfacial material


- Critical parameters controlling dry friction:
 - Shear strength of interface: τ

 Depends on the nature of interfacial material
 - Load carrying capacity of the substrates: P
 Elastic deformation as well as roughness
 affect the contact pressure
- The nature, composition and properties of the interfacial material are thus critical for understanding friction and its evolution!



Friction-induced chemical changes: Tribochemistry

- Producing new compounds through chemical reactions require energy. Several ways to provide the energy:
 - Photon activation: photochemistry
 - Electrical activation: electrochemistry
 - Thermal activation: thermochemistry
 - Stress-induced activation: mechano-chemistry





Contacts are « chemical reactors » where reactions may take place between the counterfaces and/or with the environment



Friction-induced chemical changes: Tribochemistry

- Tribochemistry: some specificities though!
 - Reacting species must be "close enough"
 - Stress distribution in a real contact is highly heterogeneous
 - Nature of reaction products will affect tribological response
 - ⇒ Complex structure of the "tribofilms" with lateral and vertical gradients







Example of tribofilm growth on steel from an anti-wear lubricant additive, Zinc dialkyl-dithiophosphate (ZDDP or ZnDTP)



Friction-induced chemical changes: Tribochemistry


- Competition between stress activation and catalysis
 - Due to wear, new surfaces are exposed: "nascent surfaces"
 - Presence of metal or oxides may affect chemical processes
 - Yet experiments with Atomic Force Microscopy (AFM) clearly evidence a stress and temperature activation







Key tribological parameters



Intrinsic parameters: Materials

Surfaces & interfaces

- Composition & chemistry
- Roughness

Coatings

- Composition & chemistry
- Structure & thickness
- Adhesion to substrate
- Mechanical properties

Substrates

- Composition & chemistry
- Structure
- Mechanical properties

Extrinsic parameters: System

Contact parameters

- Geometry & applied forces
- Contact pressure

V Kinematic parameters

- Nature of relative motion
- Speed, length
- Frequency of exposure

Environmental parameters

- Nature & pressure of gases or presence of liquid
- Temperature
- External solid particles



Adjusting contact severity...

Geometry

- Point contact / Line contact / Surface contact
- Increasing apparent contact area
- Decreasing contact pressure

Applied force

- Affects contact area and pressure
- Contact computations: Hertz, K.L. Johnson...
- Maximum stress beneath the surface

Sliding velocity / contact frequency

- Contact temperature
- Kinetics of tribochemical reactions

Environment

- Nature & reactivity of the environment
- Imposed temperature




Playing with kinematics...

- Different type of motion: linear, rotating / continuous or reciprocating
- **Dwell time**: time between passes may affect chemical reactions with environment
- **Kinematic lengths** of both counterparts: asymmetric nature of most tests!
 - Linear ball-on-flat case



lacksquare Distance traveled by a point on the flat: $L_{flat} = 2a \cdot N$




Rotating ball-on-disk case





With
$$2a=100~\mu m$$
 & $R=15~mm$, ratio: $\frac{L_{ball}}{L_{flat}}=\frac{2\pi R}{2a}\simeq 1000$





Surfaces & Friction Solid lubrication processes of Diamond-Like Carbon

Part 3

Laboratoire de Tribologie et Dynamique des Systèmes

LTDS UMR 5513

http://ltds.ec-lyon.fr









Solid lubrication processes of Diamond-Like Carbon


- **▼** Introduction to DLC coatings
- **Role of surface chemistry**
- Role of surface topography
- **▼** Interactions with environment
- **Discussion & summary**



Diamond-Like Carbon: Popular tribological coatings...













- DLC: a family of hard amorphous carbon films
- Provide low friction and wear:
 good performances as solid lubricants
- Many industrial applications...



... An amorphous carbon structure...





Random covalent network model of hydrogenated amorphous carbon films


Angus et al. (1992)

- Metastable amorphous DLC structure:
 - "Random Covalent Network" of sp² C, sp³ C, H
 ... with defects: dangling bonds, entrapped H₂ or CH₄...
 - Clustering of sp² C: aromatic rings (6-fold C rings)
 ... with defects: 5- or 7- fold rings (non planar clusters...)
 - Graphite is the stable form of carbon, but high disorder may hinder long-range ordering



... With versatile properties...

- Large variety of DLC coatings:
 many different structures & compositions
 depending on deposition process ...
 ⇒ wide range of properties
 - Physical Vapor Deposition (PVD) for hydrogen-free a-C and ta-C
 - Chemical Vapor Deposition (CVD) for hydrogenated a-C:H and ta-C:H




Hydrogen content	< 1 to > 50 at.%		
Percentage of sp ³	20 to 90%		
Optical gap	0.4 to 4 eV		
Compressive stress	up to few GPa		
Surface energy	$< 20 \text{ to} > 60 \text{ mN.m}^{-1}$		
Thermal stability	up to ~300°C		

a-C	a-C:H	ta-C	ta-C:H
10 - 20	2 - 30	25 - 70	25 - 60
150 - 200	50 - 250	200 - 650	150 - 300
0.08 - 0.1	0.1 - 0.16	0.1 - 0.2	0.16 - 0.2
	10 - 20 150 - 200	10 - 20 2 - 30 150 - 200 50 - 250	a-Ca-C:Hta-C10-202-3025-70150-20050-250200-6500.08-0.10.1-0.160.1-0.2

- As hard or harder than steel or most metallic substrates
- Comparable or lower elastic modulus (except high sp³ content ta-C)
- ✓ Higher H/E ratio (~ strain to failure)



... But a tribological paradox!



Archard's law

The harder the more wear-resistant Nitrides, carbides, ceramic coatings

$$V_{worn} = \frac{k}{H} \cdot F_n \cdot L$$

♥ Bowden & Tabor

Easy shear thin film trapped between hard and stiff substrates Soft metals, lamellar solids...


$$F_t = A_r \cdot \tau$$

How can DLC be both hard and easy to shear?



... Yet some limitations!

- Strong sensitivity to environment and coating composition!
- Versatility of the tribological performance...
 ...dependence on deposition process parameters





Solid lubrication processes of Diamond-Like Carbon

- **▼** Introduction to DLC coatings
- Role of surface chemistry
- Role of surface topography
- **▼** Interactions with environment
- Discussion & summary



Tribological experiments on "model" DLC

Analytical UHV tribometer

Linear reciprocating motion

DLC (1 µm) on Si(100)

Environment: UHV (<10-6 Pa) or pure gases

Sliding speed: 0.5 mm/s


Pin material: 52100 bearing steel


Pin radius: 8 mm Normal force: 3-5 N

Max. Hertz pressure: ~550 MPa

Contact width ~100 µm

Macroscopic contact






Donnet & Grill, Surf. Coat. Technol. 1997 Donnet et al., J. Appl. Phys. 1999 Bec et al., Phil. Mag. 2006



Friction of a-C:H in UHV



Comparison of these 2 a-C:H films

AC8: 34 at.% of H – **AC5:** 40 at.% of H

Superlow friction is achieved $(\mu < 0.01)$

For AC8, drastic friction increase occurs after few tens of cycles (> x100)

For *AC5*, small friction increase occurs after few hundreds of cycles (< x10)


Tribofilm is formed during running-in

Drastic friction increase correlated with **removal of tribofilm**

Key-role of hydrogen content?




Surface chemistry & tribofilm build-up






Key role of tribofilm build-up

Tribofilm grown on metallic counterface






- Weak interactions between carbon-based sliding surfaces
 - Reduced adhesion if enough hydrogen on the surface? (or "passivating" species)
 - Avoiding strong bonds: covalent or metallic



Critical surface coverage by hydrogen?

Surface coverage by Hydrogen would explain superlow friction of a-C:H under ultra-high vacuum?

"Stabilized" UHV friction coefficient (after 500 cycles)



3 different PECVD processes

HDP: rf-PECVD from $C_2H_2 + H_2$ **IBM:** dc-PECVD from C_6H_{12} or C_2H_2

HEF: dc-PECVD from C_2H_2 (PVD Ti-based underlayers)

HDP: 26-30 at. %

IBM: 34-40 at. %

HEF: ~ 46 at. %



Threshold in hydrogen content depends on deposition process


How could we have similar hydrogen coverage with such different hydrogen contents?



Loss of superlow friction...

Triboscopy: "friction maps"

Friction as a function of position and number of cycles



Loss of "superlow" friction:

- Start at localized points of the wear track
- Quickly extends to an entire cycle

⇒ due to adhesive phenomena



The key-role of adhesive phenomena

- Positive role of adhesive phenomena:
 - → promote tribofilm build-up and friction reduction
- ▼ Negative role of adhesive phenomena:
 - → may lead to drastic friction increase
- Adhesion seem to control the friction of DLC
 - → related to surface chemistry?





Soefficient of friction

Surface chemistry & adhesion

Strong adhesion

- "Dangling" σ bonds
- $\nabla \pi$ orbitals interactions? Metallic bonding?





Intermediate adhesion

Critical role of water vapor

- ▼ Hydrogen bonding?
- ▼ Capillarity?

Weak adhesion

- Hydrogen-terminated surfaces
- ▼ Van der Waals interactions



Solid lubrication processes of Diamond-Like Carbon

- Introduction to DLC coatings
- **Role of surface chemistry**
- Role of surface topography
- **▼** Interactions with environment
- **Discussion & summary**




A closer look at running-in...

Running-in: only due to tribofilm build-up?

UHV friction experiments with:

- **▼** 5 different positions on the DLC coated flat
- Same position on the steel pin
- ▼ 300 cycles at each flat position




Systematic running-in from > 0.02 during > 15 cycles...
Something has to change on DLC surface!




Investigating surface morphology

AC5
0 cycles

 $R_a = 2.7 \text{ nm}$ $R_q = 3.4 \text{ nm}$





AC5 500 cycles


 $R_a = 1.4 \text{ nm}$ $R_q = 1.9 \text{ nm}$

 $\mu \simeq 0.25$


AC8
0 cycles

 $R_a = 1.8 \text{ nm}$ $R_q = 2.4 \text{ nm}$









 $\mu \simeq 0.003$

AC8 80 cycles


 $R_a = 1.3 \text{ nm}$ $R_q = 1.6 \text{ nm}$

- Topography observed by SEM and measured by AFM
- Both samples exhibit roughness at nanoscale
- Partial wear of asperities is necessary to reach superlow friction
- Wear of AC8 asperities seems faster than AC5



Surface smoothening & adhesion

What happens near the high friction areas?




Smoothening of nanoscale roughness leads to large adhesive phenomena Why such different friction evolution between these two coatings?




Consequences of adhesion

SEM / EDX observations of wear tracks on the AC8 flat:

- Some cracks can be found in the DLC around transferred iron particles
- ▼ Deep grooves are then formed from these "adhesive junctions"
- **▼** Adhesion is clearly controlling the loss of superlow friction for AC8









Consequences of adhesion

SEM / EDX observations of tribofilm on counterface of AC5:

- ▼ Tribofilm doesn't appear to be continuous!
- ▼ Many "dots" of carbon-based materials are covering the steel surface
- ▼ Much thicker tribofilm is found in high friction areas
- **♥** Growth of tribofilm results from the release of adhesive junctions










Key-role of mechanical properties


Mechanical properties of DLC control how adhesive junctions will break :



SOFTER AC5: H = 7.5 GPaViscoplasticity: 6.8 10-2









HARDER AC8:
H = 10.5 GPa
Viscoplasticity: 1.4 10-2







Solid lubrication process of DLC






Solid lubrication processes of Diamond-Like Carbon

- Introduction to DLC coatings
- **Role of surface chemistry**
- Role of surface topography
- Interactions with environment
- Discussion & summary



Environment-controlled experiments on SiO_x-DLC



Si wafer coated with a-C:H:Si:O

C: 57±3 at.% H: 34±3 at.%

Si: 6±1 at.% O: 3±1 at.%

Fraction of sp²-bonded C: 54±2% (NEXAFS)

Thickness: 1.9±0.1 µm

Roughness (rms): 1.4±0.1 nm

(over 5x5µm²)

 $H = 10 \text{ GPa} - E^* = 140 \text{ GPa}$

Experimental conditions

Materials: Steel pin, Si-coated flat

Experiments under O_2 :

0.01 mbar up to 1000 mbar

Experiments under H₂:

0.01 mbar up to 2000 mbar

Pin diameter: 8 mm


Sliding Speed: 0.5 mm/s

Applied load: 3 N (≈ 430 MPa)

Track's length: 2 mm




Friction evolution in H₂ & O₂



- HV and low gas pressure: very high friction
- With higher pressures of O₂ or H₂: *lower friction*
- Computing an average coefficient of friction



Threshold in gas pressure to achieve low friction



- Clear threshold between high and low friction
- At least 14 mBar of O₂ or 10 to 50 mBar of H₂ is required



HV and low pres


High pressure


Transfer phenomena triggered by gas pressure



a-C:H:Si:O flat

Steel pin







Breakage of adhesive junctions not only controlled by mechanical properties!



LTDS Near-edge X-ray absorption fine structure (NEXAFS)






Acquisition of images...

rack #4 (HV) Track #3 (O, 15 mbar) Oxygen Track #2


Partial Electron Yield (A.u.)



Photon Energy (eV)




NEXAFS spectra on wear tracks



- Differential spectra by subtracting non-contact region spectrum (remove contribution of adventitious carbon)
- At 285 eV: strong sp² C increase
- Rehybridization due to C–C bond breaking?




NEXAFS images of wear tracks




Decreasing sp² fraction with increasing gas pressure for both H₂ and O₂
 ⇒ rehybridization decreases

Increasing C–H bonds in H₂, but slightly decreasing C–O & C=O bonds in O₂
⇒ surface passivation or not?






A look at environment effect on wear



- ✓ Just above the threshold, higher wear in H₂ than in O₂
- When increasing gas pressure:
 - Wear decreases in H₂
 worn area becomes narrower than contact width!
 - Wear increases in O2
- Consistent with less C–C bond breaking in H₂, indeed!
- For O₂, are volatile species formed (CO, CO₂...)? Is there a gradient in sp² C near the surface?



A tentative tribological model for a-C:H:Si:O





Solid lubrication processes of Diamond-Like Carbon

- **▼** Introduction to DLC coatings
- **Role of surface chemistry**
- Role of surface topography
- **▼** Interactions with environment
- Discussion & summary



Tribology of DLC: multi-physical aspects

Solid lubrication processes of DLC coatings seems to be controlled by:

Physical interactions

- Van der Waals forces (H-terminated surface)
- Hydrogen bonding (with water vapor)
- ∇ Overlap of π -orbitals (for low H coverage) or even metallic bonding?
- Physisorption of environmental gases?
- Contribution of electrostatic interactions?

Chemical reactions

- Covalent bonding between sliding surfaces
- "Passivation" of dangling bonds by environmental gases
- Controls the nature of sliding surfaces...

Surface mechanical behavior

- Controls the real area of contact
- Controls the release of adhesive junctions
- ✓ Not only hardness to be considered: viscoplasticity, fracture toughness...
- ▼ Role of time-dependance of mechanical properties?
- Importance of ductile/brittle transition?



Tribology of DLC: multi-scale aspects

Solid lubrication processes of DLC coatings take place at different scales:


- At the scale of molecules...
 - Adhesive phenomena are controlled by physical interactions & chemical reactions
- At the scale of asperities...
 - ▼ Nanoscale surface topography controls the size of adhesive junctions
 - Mechanical behavior of asperities controls friction & wear
- At the scale of the coating...
 - Mechanical properties control the real area of contact
 - When large adhesive junctions are formed, they also control future evolution of the contact: where are these junctions released?




Few open questions on tribology of DLC...

- **♥** How are nanoscale adhesive junctions released?
 - Asperities on harder AC8 are worn much quicker than on softer AC5!
 - Difference in "toughness" of the asperities?
 - "Healing phenomena" thanks to time-dependant mechanical properties?
- What is the frequency of contact for an asperity, and its average contact time/length?
 - This might control passivation of dangling bonds as well as "viscous" recovery of asperities...
- What is the critical size of adhesive junctions to have surface damage and friction increase?
 - Is there a size effect on some kind of "ductile/brittle" transition?
 - Small junction would have plastic behavior, while large ones would lead to cracking?
- What is the effect of environment on mechanical behavior of asperities?
 - If asperities are sheared, bonds should break and may react with environmental gases...







A new environment-controlled tribometer

- Based on a custom 6 axes sensor (Forces: 1 mN up to 15 N)
- 4 motion axes: X, Y, Z, Rz
- ▼ Environment: from 10-9 mBar to 1 atm
- Temperature: -120 to 600°C



Sample holder with electrical and mechanical connections going through the sensor


Final stage

Capacitive sensor target

Capacitive sensor


Fixed stage






- Linear reciprocating ball-on-flat experiment
- Similar conditions as previous studies (5 N, 2 mm @ 1 mm/s...)
- Sample AC5 as in previous studies: similar results...
- ▼ Drastic improvements in the signal/noise ratio!





#	Initial tribofilm	Load	Length	Cycles	Orientation
1	No	3 N	2 mm	500	0°
2	Yes	5 N	2 mm	500	0°
3	Yes	5 N	2 mm	1000	0°
4	Yes	5 N	2 mm	500	90°
5	yes	5 N	3 mm	500	45°



1.5

2

-0.01

0.006

Crossing previous sliding tracks to probe surface modifications


200

0.5

Position (mm)

- Significant friction decrease when crossing previous tracks
- It confirms that changes on the flat are necessary, friction decrease is not only due to tribofilm build-up






A: Friction on fresh area without previous tribofilm

B: Friction on fresh area with pre-existing tribofilm

C: Crossing of previous tracks with pre-existing tribofilm

- Pre-existing tribofilm: initial friction reduced by 32%
- Previous wear on the flat: *initial friction further reduced by* 36%
- Drastic shortening of the transient regime leading to low friction





Thank you for your attention!

Laboratoire de Tribologie et Dynamique des Systèmes

LTDS UMR 5513

http://ltds.ec-lyon.fr





