

STATIC AND DYNAMIC MAGNETIC IMAGING USING X-RAY BASED TECHNIQUES

Victor Ukleev Spin and Topology in Quantum Materials Helmholtz-Zentrum Berlin für Materialen und Energie, Germany

Advanced Microscopy techniques for characterizing the magnetic properties of materials

EPFL Switzerland 16.11.2022

OVERVIEW


- Introduction:
 - •x-ray absorption and x-ray magnetic dichroism
 - resonant x-ray absorption and scattering
 - polarized x-ray sources and beamline optics
- Classic x-ray magnetic imaging techniques
 - Photoemission electron microscopy (PEEM)
 - Transmission x-ray microscopy
- State-of-the-art techniques
 - Coherent x-ray diffraction imaging and holography
 - Three-dimensional x-ray imaging
 - Time-resolved magnetic x-ray imaging with synchrotrons and free-electron lasers
- Summary




Polarization-dependent x-ray absorption

- L-edges of transition metals: probes valence states and magnetism
- Peak corresponds to transition from core level to valence band
- Soft x-rays: ~100 eV ... ~2 keV
- Due to the symmetry of the transition operator we obtain the dipole selection rules: Δs=0 Δl=±1 -> orbital and spin
 moment selectivity

 Mn L edge





Photon Energy (eV)

630 635 640 645 650 655 660 665 670

Photon Energy (eV)

Photon Energy (eV)

Normalized Intensity

7+

2+/3+

X-ray Circular Magnetic Dichroism (XMCD)

Theoretical prediction -> 1975

PHYSICAL REVIEW B

VOLUME 12. NUMBER 11

1 DECEMBER 1975

Calculation of the M_{23} magneto-optical absorption spectrum of ferromagnetic nickel

J. L. Erskine*

Department of Physics, University of Illinois, Urbana, Illinois 61801

E. A. Stern[†]

Department of Physics, University of Washington, Seattle, Washington 98195 (Received 28 April 1975)

Experimental observation -> 1987

VOLUME 58, NUMBER 7

PHYSICAL REVIEW LETTERS

16 FEBRUARY 1987

Absorption of Circularly Polarized X Rays in Iron

G. Schütz, W. Wagner, W. Wilhelm, and P. Kienle (a)

Physik Department, Technische Universität München, D-8046 Garching, West Germany

R Zelle

Institut für Festkörperforschung der Kernforschungsanlage Jülich, D-5175 Jülich, West Germany

an

R. Frahm and G. Materlik

Hamburger Synchrotronstrahlungslabor am Deutsches Elektronen-Synchrotron DESY, D-2000 Hamburg 52, West Germany (Received 22 September 1986)

Polarization-dependent absorption of circularly polarized x-rays by magnetic materials (magnetic atoms)


- Element-specific magnetic contrast
- Spin and orbital moment selectivity
- Very high sensitivity


 X-ray techniques can be transferred into it's magnetic counterpart, by tuning the x-ray energy to a corresponding XMCD sensitive edge: microscopy, spectroscopy, diffraction, reflectometry, small-angle scattering, etc.





X-ray magnetic circular dichroism (XMCD)


Circular dichroism - a tool to study ferro(ferri)magnets



















$$I(z) = I_0 e^{-\mu_x z}$$

where μ is material-specific coefficient dependent on photon energy

XMCD microscopy and scattering


250nm



X-ray magnetic linear dichroism (XMLD)

Linear dichroism - a tool to study antiferromagnets

- XMLD is sensitive to the antiferromagnetic order: spin orbit coupling breaks spherical symmetry of the charge density
- XMLD is quadratic to magnetization
- Similarly to XMCD allows to employ magnetic and element-selective imaging




INTRODUCTION


X-ray resonant magnetic scattering (XRMS)


- Same transition is used to observe resonant scattering and diffraction: $L_{2,3}$ edges of TM correspond to soft x-rays in the energy range of 480 950 eV, $\lambda \sim 15-20$ Å
- Resonant x-rays allow both reciprocal (scattering) and real-space (imaging)

Thickness: transmission vs magnetic scattering intensity


$$I_{mag} \sim M^2 = (\mu A z)^2$$
$$I_{trans} = I_0 exp(-l_{att} z)$$








Zhang, S. L., Nat Comm. 8.1 (2017)









Polarized synchrotron x-rays

Polarised synchrotron radiation by bending magnets and insertion devices (IDs)



INTRODUCTION

X-ray optics



(A) Kirkpatrick–Baez (KB) mirror system

Diffraction, spectroscopy, etc.

(B) compound refractive lenses (CRL)

High energy x-rays


(C) Fresnel zone-plates (FZP) Microscopy, nano-spectroscopy

X-ray Optics	CRLs	Fresnel ZP	KB Mirrors
ZP-equivalent Numerical Aperture (based on outermost zone; smaller is better)	30 nm	30 nm	16 nm
Achievable Focus Resolution (Typical Value Best Possible)	Very High (1 µm <30 nm)	Very High (200 nm 10 nm)	Very High (1 µm 20 nm)
Handling/Ease of Alignment (Compact)	✓	✓	×
Achromatic	×	×	4
Working Distance Range Selection	5 mm – 10's m	1 mm – 30 mm	10 cm – 10's m
Efficiency	~50%	~10%	~75%
In-line with Beam	4	✓	×
Price (including beamline costs & motion control systems)	Depends	High	Mid to High (long beamline & stability

Cotte, M., et al., Comptes Rendus Physique 19.7 (2018): 575-588 https://www.sigray.com/


INTRODUCTION


X-ray optics



Alternate 'zones' modify phase/amplitude of incident wavefront:

for material of thickness (t), wavelength (λ), refractive index (1- δ -i β), the phase shift $\Delta \varphi$, is: $\Delta \varphi = 2\pi \delta t/\lambda$





λ (nm)	Material	δ	β	Thick [†] (nm)	Transmission
13.5	Ru	0.113	0.017	59-7	0.38
13.5	Mo	0.076	0.0064	88.8	0.59
0.155 (8 keV)	Si	7.67e-6	1.77e-7	10000	0.86
0.155 (8 keV)	Au	4.77e-5	4.96e-6	1600	0.52


http://zoneplate.lbl.gov/theory

Barrett, R., X-ray Optics for Synchrotron Radiation Beamlines (ESRF)

on the ZP and the x-ray wavelength


X-ray detection

Photoemission electron microscopy (PEEM)




Transmission x-ray microscopy (TXM), scanning TXM, holography, coherent diffraction imaging, ptychography, etc.

X-ray photoemission electron microscopy (PEEM)






X-ray photoemission electron microscopy (PEEM)




Aperture size and resolution




X-ray photoemission electron microscopy (PEEM)


Magnetic domains




FM (0.7 nm Co) AFM (LaFeO₃)



Artificial spin ice




A. Scholl / Current Opinion in Solid State and Materials Science 7 (2003) 59-66




X-ray photoemission electron microscopy (PEEM)

Vector mapping of magnetization




$$I_{\text{XMCD}} = (I_{\sigma^+} - I_{\sigma^-})/(I_{\sigma^+} + I_{\sigma^-}) = \mathbf{M} \cdot \mathbf{K} = \langle \mathbf{M} \rangle \cos(\alpha)$$


Patterned FiM GdFeCo nanostructure




L. Le Guyader et al., Journal of Electron Spectroscopy and Related Phenomena 185 (2012)




Transmission x-ray microscopy



XMCD contrast in transmission









Scanning transmission x-ray microscopy

Beamline layout (PolLux, Swiss Light Source, PSI)




STXM scheme




Roesner, B, et al., Optica 7, 11, 1602 (2020)

7 nm is the highest resolution achieved


XMCD contrast in transmission






Scanning transmission x-ray microscopy

XMCD contrast in transmission




Need thin samples!



Transparent Si₃N₄ membranes



FeGd multilayer grown on Si₃N₄





Film deposition

Cryogenic imaging →












Phase problem

- X-ray scattering factor: $f^n = f^c i f_1^m$ is **complex**
- Scattering is a Fourier transform of the real-space density, but the measured intensity $I = |F(f^n)|^2$ is **real**


charge magnetic
$$f^{n} = (\mathbf{e}_{n} \cdot \mathbf{e}'_{n})f^{n}_{c} + i(\mathbf{e}_{n} \times \mathbf{e}'_{n}) \cdot \mathbf{M}^{n}f^{n}_{m1} + (\mathbf{e}_{n} \cdot \mathbf{M}^{n})(\mathbf{e}'_{n} \cdot \mathbf{M}^{n})f^{n}_{m2}.$$

- Coherence-based methods allow to solve the phase problem and reconstruct the real-space image
- Coherent diffraction imaging, holography, ptychography, interferometry, etc.




Coherent x-ray scattering / imaging

- X-ray scattering factor: $f^{res} = f^c i f_1^m$ is **complex**
- Measured intensity $I = |F(f^{res})|^2$ is **real**



- Coherence-based methods allow to solve the phase problem and reconstruct the real-space image
- Coherent diffraction imaging, holography, ptychography, etc.

Coherent x-ray scattering / imaging





More detailed lectures on coherence-based technique are available at LINXS CoWork channel:

- 1) Introduction to CDI by Prof. Pablo Villanueva-Perez, https://www.youtube.com/watch?v=RnBnwaYpgk8
- 2) CDI principles and algorithms by Dr. Tomas Ekeberg, https://www.youtube.com/watch?v=N3bbGsEApzE
- 3) Bragg CDI by Dmitry Dzhigaev, https://www.youtube.com/watch?v=jiY9e4pl2t0
- 4) Ptychography by Virginie Chamard, https://www.youtube.com/watch?v=LEfmq1afQo8
- 5) Algorithms in Bragg CDI by Prof. Ian Robinson, https://www.youtube.com/watch?v=MabspCO3yUs

Coherent x-ray scattering / imaging

- Measured intensity $I = |F(f^{res})|^2$
- Iterative phase retrieval can be used is the sample size is smaller than the coherent size of the beam (oversampling ratio σ >2)







$$\mathrm{PRTF}(\mathbf{u}) = \frac{|\mathcal{F}_{\mathbf{u}}\{\bar{\gamma}_M\}|}{\sqrt{I(\mathbf{u})}} = \frac{\left|\langle \Gamma_M(\mathbf{u}) \mathrm{exp}(i\,\phi_0)\rangle\right|}{\sqrt{I(\mathbf{u})}}$$

Real-space resolution estimated from PRTF d<50 nm (~ 30-40 nm) without focusing optics

Coherent x-ray scattering / imaging

- Measured intensity $I = |F(f^{res})|^2$
- Iterative phase retrieval can be used is the sample size is smaller than the coherent size of the beam (oversampling ratio σ >2)





Estimate of the resolution is given by the frequency at which the PRTF reaches a value of 0.5.

Ukleev, V., et al., Quant. Beam. Sci. 2 (2018)

$$PRTF(\mathbf{u}) = \frac{|\mathcal{F}_{\mathbf{u}}\{\overline{\gamma}_M\}|}{\sqrt{I(\mathbf{u})}} = \frac{|\langle \Gamma_M(\mathbf{u}) \exp(i\,\phi_0) \rangle|}{\sqrt{I(\mathbf{u})}}$$

Real-space resolution estimated from PRTF d<50 nm (~ 30-40 nm) without focusing optics




Fourier transform holography

• Phase problem can be solved with the amplitude modulation by a reference wave:

$$\mathscr{F}^{-1}\left\{|F(u,v)|^2\right\} = f \otimes f = o \otimes o + r \otimes r + o \otimes r + r \otimes o,$$

Real-space reconstruction via single Fourier transform

STXM image



20 µm pinhole


Mask and sample

Au mask

SiN_x membrane Magnetic film

FTH

SEM



Distance (nm)

Note: x-ray holography \neq electron holography

Fourier transform holography (FTH) with a reference hole is limited by the intensity/resolution ratio



Fourier transform holography and HERALDO


• Phase problem can be solved with the amplitude modulation by a reference wave:


The phase is encoded in the interference pattern (object and reference)

$$\mathscr{F}^{-1}\left\{|F(u,v)|^2\right\} = f\otimes f = o\otimes o + r\otimes r + o\otimes r + r\otimes o,$$

Derivative of the step function is two delta functions


$$\mathcal{L}^{(n)}\{f \otimes f\} = \frac{1}{2}(-1)^n \left[A^* r(x + x_0, y + y_0) + r \otimes g \right] + \frac{1}{2} \left[A r^* (x_0 - x, y_0 - y) + g \otimes r \right]$$
$$+ \mathcal{L}^{(n)}\{o \otimes o\} + (-1)^n o \otimes g + g \otimes o + (-1)^n A^* o(x + x_0, y + y_0) + A o^* (x_0 - x, y_0 - y)$$





Reference slit can improve the contrast compared to reference hole without loosing the resolution

Guizar-Sicairos, M. and Fienup, J.R., 2007. Holography with extended reference by autocorrelation linear differential operation. Optics express, 15(26), pp.17592-17612.





Fourier transform holography (FTH) with a reference hole is limited by the intensity resolution ratio





Holography with extended reference (HERALDO)


HERALDO example: skyrmion host Co₈Zn₈Mn₄











Aperture size: *d*=700 nm

Slit size:

 $w=0.04 \mu m, l=1 \mu m$




Holography with extended reference (HERALDO)

• Phase problem can be solved with the amplitude modulation by a reference wave:

$$\mathscr{F}^{-1}\left\{|F(u,v)|^2\right\} = f \otimes f = o \otimes o + r \otimes r + o \otimes r + r \otimes o,$$


Real-space reconstruction via Fourier transform an linear differential operator (HERALDO)






X-ray ptychography

Taking coherent scattering patterns from overlapping regions using FZP



15 nm real-space resolution imaging of magnetic domains in SmCo₅




- Reconstruction algorithm similar to CDI
- Ptychography can be used to study extended objects


Shi et al. Appl. Phys. Lett. 108, 094103 (2016)

X-ray holography in reflection

Holographic mask is placed after reflected beam




- So far only demonstrated only for charge patterns...
- Ptychography is also possible
- ~60 nm resolution






X-ray imaging in three dimensions


Hard x-ray resonant tomography (Gd L_3 edge)





- High energy allows transmission of a few tens µm
- Ptychographic scans are measured for multiple projections to reconstruct 3D magnetization vector distribution

0.182 0.005 0.17 -0.005 **XMCD** Circularly polarized




Donnelly, C., et al., Phys. Rev. B 94, 064421 (2016)

Donnelly, C., et al., Nature 547, 328–331(2017)



X-ray imaging in three dimensions



Reconstruction of the magnetic structure of a permalloy nanodisc

- Naturally thin or nanofabricated samples
- Multiple projections to reconstruct 3D magnetization vector distribution measured with single rotation axis
- Challenging to introduce complex sample environment


Great talk by Claire Donnely on 3D imaging (LINXS seminar) https://www.youtube.com/watch?v=K4jQlE0HaHs





Time-resolved imaging


Stroboscopic pump-probe imaging: synchronized x-ray and excitation pulses (magnetic field, laser pulses, etc.)

Sub-100 ps imaging of *periodic* phenomena PEEM, STXM, holography, 3D methods, etc.










Time-resolved imaging

Time resolution is limited by the pulse duration Need high-flux x-ray source with fs pulses to study spin dynamics at atomic scales: x-ray free-electron laser



Please, watch this (5min) movie about SwissFEL https://www.youtube.com/watch?v=P2CG69hRYR8


Time-resolved imaging

Time resolution is limited by the pulse duration


Need high-flux x-ray source with fs pulses to study spin dynamics at atomic scales:

x-ray free-electron laser

XFEL experiment@LCLS: single-shot imaging



Damage of the spin structure by the pulses longer than 80 ps! -> non-linear interaction of x-rays with electronic order




Wang, T., et al., PRL 108, 267403 (2012)


Time-resolved imaging

Time resolution is limited by the pulse duration Need high-flux x-ray source with fs pulses to study spin dynamics at atomic scales: x-ray free-electron laser

Synchrotron-based FTH imaging:



Nucleation of magnetic skyrmions by optical laser pulses: time scale >10 ps





Comparison to other magnetic imaging techniques

Method	Probe	Spatial resolution	Temporal resolution	Magnetization direction	Sample type	Instrument type
Kerr microscopy	Optical photons	Fair (>300 nm)	Very good (fs)	Any	Surface (Kerr) Thin film (Faraday)	Lab.
Lorentz TEM (+DPC, holography, etc.)	Electrons	Very good (<10 nm)	Good (ps)	In-plane	Thin film	Lab.
MFM	Cantilever	Good (10-100 nm)	Bad (min)	Out-of-plane	Surface	Lab.
Neutron imaging	Neutrons	Bad (μm)	Bad (min)	Any	Bulk	Neutron source
PEEM	X-rays + Electrons	Good (10-100 nm)	Good (ps)	Out-of-plane (NI) In-plane (GI)	Surface	Synchrotron
STXM (+ holography, ptychography, etc.)	X-rays	Good (10-100 nm)	Good (ps)	Out-of-plane	Thin film 'thinned bulk' <1 µm	Synchrotron


Where?

Lightsources of the World



Where?

...and of Europe



https://www.wayforlight.eu/



Facility	Deadline
CHESS (USA)	2022/12/20
Pohang XFEL (Korea Rep.)	2022/12/31
Canadian Light Source (Canada)	2022/12/31
European XFEL (Germany)	2022/12/29
MAX IV (Sweden)	2023/02/28
ESRF (France)	2023/03/01
PETRA-III (Germany)	2023/03/01
BESSY-II (Germany)	2023/03/01
APS (USA)	2023/04/17
SwissFEL (Switzerland)	2023/06/30
ALS (USA)	2023/07/31
SLS (Switzerland)	to be announced (SLS 2.0 upgrade is upcoming)

Committee decision ~2-3 months after the proposal submission deadline Beamtime ~4-12 months after the proposal submission deadline



Beamlines (example)

Method	Beamline	Facility	Energy range	Magnetic field	Temperature range
PEEM	SIM SPEEM@UE49-PGM 106 CIRCE HERMES	SLS PSI, Switzerland BESSY II, Germany Diamond, UK ALBA, Spain SOLEIL. France	90-2000 eV 100-1800 eV 100-1300 eV 100-2000 eV 70-2500 eV	~100 mT ~100 mT available available available	120-800 K 45-600 K 100-1900 K 100-1500 K 150-2000 K
TXM	MISTRAL	ALBA, Spain	270-1200 eV	2 mT	105-300 K
	SPEEM@UE41-PGM	BESSY II, Germany	180-2800 eV	no	100-300 K
STXM	POLLUX	SLS PSI, Switzerland	250-1600 eV	200 mT	280-400 K
	HERMES	SOLEIL. France	70-2500 eV	20 mT	150-600 K
	MAXYMUS	BESSY II, Germany	200-1900 eV	250 mT	30-350 K
Holography / coherent diffraction imaging in transmission	ALICE-2	BESSY II, Germany	depends on beamline	700 mT	10-350 K
	COMET@SEXTANTS	SOLEIL, France	50-1700 eV	1000 mT	30-800 K
	MaReS@BOREAS	ALBA, Spain	50-4000 eV	2000 mT	20-400 K

Summary

- Real-space imaging of magnetization down to (sub)10 nm is possible using resonant x-rays
- Element selectivity is naturally provided
- Complex sample environment (high vacuum, cryogenic temperatures, magnetic fields, optics, etc.)
- Naturally thin or nanofabricated samples or surfaces
- Coherent imaging has great potential to push the resolution to ~1 nm limit
- Three-dimensional imaging is possible
- Time-resolved imaging (sub-100 ps routinely, fs time scale at FELs) is possible

Further reading/watching

• Fundamentals of magnetic dichroism, sum rules, etc.

Stöhr, J. "X-ray magnetic circular dichroism spectroscopy of transition metal thin films." Journal of Electron Spectroscopy and Related Phenomena 75 (1995): 253-272. van der Laan, G., and Figueroa, A. I.. "X-ray magnetic circular dichroism—A versatile tool to study magnetism." Coordination Chemistry Reviews 277 (2014): 95-129.

Resonant x-ray scattering

Fink, J., et al. "Resonant elastic soft x-ray scattering." Reports on Progress in Physics 76.5 (2013): 056502. Paolasini, L., and de Bergevin F. "Magnetic and resonant X-ray scattering investigations of strongly correlated electron systems." Comptes Rendus Physique 9.5-6 (2008): 550-569.

X-ray magnetic imaging

Fischer, P.. "Magnetic imaging with polarized soft x-rays." Journal of Physics D: Applied Physics 50.31 (2017): 313002. Reeve, R. M., et al. "Magnetic imaging and microscopy." Handbook of Magnetism and Magnetic Materials (2020): 1-52.

Coherence

Nugent, K. A. "Coherent methods in the X-ray sciences." Advances in Physics 59.1 (2010): 1-99.

Munro, P. "Coherent x-ray imaging across length scales." Contemporary Physics 58.2 (2017): 140-159.

LINXS Webinar CoWork series on YouTube https://www.youtube.com/playlist?list=PLoa4trwK2Db7kaHauxrN9KhPYgS44Oo8Y

Dynamics

Raftrey, D., and Fischer, P. "Advanced magnetic X-ray spectro-microscopies to characterize mesoscopic magnetic materials." Journal of Magnetism and Magnetic Materials 545 (2022): 168734.

Huang, N., et al. "Features and futures of X-ray free-electron lasers." The Innovation 2.2 (2021): 100097.

HZB photon school (with practicals!)





A Practical Introduction to Photon Science

The program of this school is aimed primarily at master students and other early stage researchers in physics, chemistry, materials science, engineering, and life or environmental sciences. Students will be introduced to advanced synchrotron- and laboratory-based photon science methods that probe the physical, chemical, and electronic structures of materials as well as the function and dynamics of complex material systems. The basic and specialized lectures are given by experienced teachers, who are HZB scientists or BESSY II super-users from our partner universities and research centers.

*contingent on BESSY II is operating at a level that allows HZB employees access



TRAININGS IN:

- Synchrotron-based methods from BESSY II beamlines
- Laboratory-based methods
- Data collection, treatment, interpretation, and presentation
- How to write successful beamtime proposals



hz-b.de/photonschool