## PHYSICS OF MATERIALS



Physics School Autumn 2024

Series 4 04 October 2024

**Exercise 1 Interstitials: Fe-C** 

What is the maximum elastic distortion of the body-centered cubic iron network (iron) from introducing a carbon interstitial (atomic radius of iron = 1.24 Å)? Compare it with the distortion in the face-centered cubic iron (iron) (atomic radius of iron= 1.27 Å) and qualitatively deduce the respective carbon solubility in the two phases.




Fig. 4.1 Compact packing

## **Exercise 2 Equilibrium concentration of vacancies**

Calculate the equilibrium concentration of vacancies in a metal at constant pressure and temperature.

## **Exercise 3 Thermal expansion of aluminum**

We measure the thermal expansion of aluminum by two methods: 1) by measuring the

dilatation strain  $\overline{\phantom{a}L}$  of a sample and 2) by measuring the relative variation of the lattice  $\Delta a$ 

parameter a by X-ray diffraction. The slopes of the curves obtained with these two methods do not coincide (see Figure 4.1). Why?

The difference between these measurements at 400°C is  $\left(\frac{\Delta L}{L} - \frac{\Delta a}{a}\right) = 7.633 \cdot 10^{-6}$ 

At 600°C, it is 
$$\left(\frac{\Delta L}{L} - \frac{\Delta a}{a}\right) = 2.94 \cdot 10^{-4}$$

Knowing these data, calculate the formation energy of vacancies in aluminum.




Fig. 4.1 Curves of the thermal expansion of aluminum measured by dilatometry and by x-ray diffraction.